

LUXAPOOL POOLSIDE & PAVING

DURABLE RUBBERISED 'SAFE SURFACE' COATING

APPLICATION ADVICE: FOR CONCRETE, STONE AND CEMENT RENDER SURFACES

1) Ensure that all surfaces are free of oil, grease or other contamination. Poolside areas should be washed with **LUXAPOOL Concentrated Wash** (500 ml dilution into 20 litres of warm water). Use stiff bristle brush or broom, then flush with fresh water. Alternatively high pressure water blast to leave a clean surface. Allow surfaces to dry to good visual standard.

2) Mask along tile lines, or otherwise at the extremity of the area(s) intended to be coated. Take additional precautions to cover pool water surfaces if at all possible.

3) Apply **Colormaker SuperSeal Primer** by 100mm minm width brush, or by medium nap roller at a spreading rate of 8 -10 sq metres per litre to thoroughly wet the surface. Allow to dry for a minm of 4 hours under summer conditions, longer in cooler conditions.

4) Apply **LUXAPOOL Poolside & Paving** using a 270mm minm width medium nap roller at a spreading rate of 2 sq metres per litre. To create a 'lower profile' lightly 'dry roll' within a few minutes of application with a fine textured roller (normally having black colour mesh). Wash the textured roller after every few sq metres of rolling, and 'flick off' excess water before re-using.

NOTE: Do NOT apply **LUXAPOOL Poolside & Paving** if rain is imminent, or if predicted within 24 hours of application. Refer to product data sheet for more detail.

5) For additional resistance to soilage, and for ease of long term surface cleaning a final coat of **Colormaker Unicryl HD Clear Glaze**. Application of such will also enrich the final colour effect, and reduce 'blocking' of heavy items later placed on the coated surface. Apply using short or medium nap roller to thoroughly wet the surface of the underlying profile. Application rate will be approximately 6 sq meters per litre dependant on surface profile. Clean all equipment with water immediately after use. Refer to the TDS for complete details. Allow to dry for minimum 12 hours before opening areas to soft sole pedestrian traffic. Full cure is achieved within 48 hours under good dry conditions.

ONGOING MAINTENANCE: Surfaces coated in accordance with the above directions should provide satisfactory long term use under typical home and environments. Some basic use and cleaning protocols should however be employed so as to maximise the service life of the coating.

Immediately clean all spillages of chemicals and non-aqueous stains. As needed, clean surfaces as using fine jet garden hose if allowed by legislation, or soft bristle broom with mild detergent wash, then flushing with fresh water.

Otherwise enjoy the long term decorative and functional benefits of your **LUXAPOOL Poolside & Paving** surface.

CMI Technical Services, Jan 2009