

LUXAPOOL POOLSIDE & PAVING

DURABLE RUBBERISED 'SAFE SURFACE' COATING

APPLICATION ADVICE: 100% POLYMER SYSTEM OVER AGED PEBBLECRETE SURFACES

- 1) Ensure that all surfaces are free of oil, grease or other contamination. Poolside areas should be washed with **LUXAPOOL Concentrated Wash** (500mL dilution into 20L of warm water). Use stiff bristle brush or broom then flush with fresh water. Alternatively high pressure water blast to leave a clean surface. Allow surfaces to dry to good visual standard.
- 2) Mask along tile lines, or otherwise at the extremity of the area(s) intended to be coated. Take additional precautions to cover pool water surfaces if at all possible.
- 3) Apply **Superseal Primer** in accordance with the TDS at approximately 8 m²/L, using a medium nap roller or airless spray. Allow to dry for minimum 4 hours, longer in cool or winter conditions. Clean equipment using **Colormaker Concrete and Paving Sealer Solvent** or **LUXAPOOL Solvent CRS**.
- 4) Apply an initial base coat of **LUXAPOOL Poolside & Paving** to the desired colour, or closest colour possible to the topcoat, aiming to fill the 'valleys of the pebblecrete profile' as opposed to leaving film thickness on the top of the profile. Application using flexible plastic trowels for the vertical surfaces and flexible rubber spreaders for horizontal surfaces has been found most satisfactory. For estimating purposes, application rate via this procedure will be approximately 1 m/L. Clean all equipment immediately after use with water. Allow to dry for minimum 8 hours, longer in cooler conditions. Refer to the TDS for full detail.
- 5) Apply the first build coat of **LUXAPOOL Poolside & Paving** to the desired colour at spreading rate of approximately 2 m/L using a medium nap roller. Within a few minutes or so of application, use a special effect metal or plastic profiling roller to achieve the desired degree of final profile. Refer to CMI for details concerning supply and use of profiling rollers. Clean all equipment immediately after use with water. Allow to dry for minimum 6 hours, preferably overnight. Allow longer dry in cool conditions.
- 6) At applicator's discretion and dependant on the degree of profiling required, Step 5) above may be repeated.
- 7) For additional resistance to soiling and for ease of long term surface cleaning, apply a finishing coat of **Colormaker Unicryl HD Clear Glaze**. Application of such will also enhance the final colour effect and reduce 'blocking' of heavy items later placed on the surface. Apply using short or medium nap roller to thoroughly wet the surface of the underlying profile. Application rate will be approximately 6 m/L dependant on surface profile.

Clean all equipment with water immediately after use. Refer to the TDS for complete details. Allow to dry for minimum 12 hours before opening areas to soft sole pedestrian traffic. Full cure is achieved within 48 hours under good dry conditions. Allow longer in cooler conditions.

ON-GOING MAINTENANCE: Surfaces coated in accordance with the above directions should provide satisfactory long term use under typical home and environments. Some basic use and cleaning protocols should however be employed so as to maximise the service life of the coating.

Immediately clean all spillages of chemicals and non-aqueous stains. As needed, clean surfaces using a fine jet garden hose if allowed or soft bristle broom with mild detergent wash, then flushing with fresh water. Otherwise enjoy the long term decorative and functional benefits of your **LUXAPOOL Poolside & Paving** surface.

CMI Technical Services
Jan 2009